



Endura-Peel WB Bright White Booth Coat *Strippable Booth Coating*

(05EPW030 / 55EPW030)

Description

Endura-Peel WB Bright White strippable booth coating is a low viscosity, zero VOC, peelable coating for paint spray-booth walls, ceilings, floors and other surfaces where paint over spray accumulation must be readily removed. Endura-Peel WB Bright White can be used as a peelable coating on steel surfaces to eliminate flash rusting or as protection on glass, Plexiglass, rubber, cement, aluminum and many other hard surfaces. Endura-Peel WB Bright White represents the ultimate in non-solvent peelable coatings. It is well stabilized against brittleness and it will not be softened or penetrated by most solvent-based paints.

Physical Properties

White opaque liquid
Weight per gallon: 9.8 lbs/gallon
Volume solids per gallon: 47%
Flash point: Not flammable
Viscosity: 8000 centipoise
Coverage: 160 sq. feet/gal at 10 mils wet (no application loss)

Product Features

Maximum operating temperature: 250°F
Bright white film for better illumination
Tough and flexible film that peels with ease
Easy application
Zero VOC

Application

Wet Film: 10-12 mils wet film to clean, dry surfaces
Airless Spray: .No reduction required. Equipment - .015 or .017 nozzle at a set pressure of 1200-1500 PSI Conventional
Roller / Brush – No reduction required.
Air-Assisted / Pressure Pot: Reduce 5% - 10% maximum with water. Equipment - Binks nozzle #68PB with needle #368 at a pressure of 35-55 PSI
Application Temperature: ambient to no lower than 60° F
Clean Up: Water

Patch Test

Because it is difficult to determine the type and condition of the surface, perform a small patch test first to confirm adhesion. It will determine the peel-ability of the coating on your particular surface, it will define the coverage and the approximate amount of time required for it to work and to remove off of surface.

Drying time

Endura-Peel WB Bright White booth coat air-dries in 10 minutes to 3 hours, depending on thickness of the coating, humidity, temperature and air movement. Endura-Peel WB Bright White booth coating cures upon water evaporation. Improved air movement and temperatures up to 130°F will cure this coating in as little as ten minutes.

Removal

Endura-Peel WB Bright White booth coat can be removed by peeling. Will turn white when wet but it will not come off unless peeled. Endura-Peel WB Bright White booth coat is water resistant when it is dry film.

Storage

Store at temperatures between 40°F - 100°F. DO NOT ALLOW LIQUID TO FREEZE. Endura-Peel WB Bright White has a shelf life of 1 year from date of manufacture.

Kenosha, WI • York, SC

(O) 800.537.5454

(F) 262.657.2210

(E) finishing-inquiry@filtrationgroup.com

<https://finishing.filtrationgroup.com>

